# 983 UV SERIES



#### 1. APPLICATION FIELDS:

Universal UV screen printing ink in a thixotropic formulation for the printing on blow moulded objects within the packaging industry, suitable for pre-treated substrates made of polyethylene (PE), polypropylene (PP), as well as for printing on paper and cardboard.

Substrates may differ in their chemical structure or method of manufacture. A test for suitability must always be carried out before printing. Antistatic, Mould Release Agents and Slip Additives may have negative effects on adhesion, and should be detected and removed prior to printing.

#### 2. CHARACTERISTICS:

This high gloss UV ink series is very reactive in nature, assuring good curing and adhesion even when printing at high machine speeds.

The inks of the 983 UV series are constitutionally free from toxic elements and solvents. The raw materials used meet with the limits stipulated by the EEC regulation EN 71 (Safety of Toys), part 3 (Migration of Certain Elements) of December 1994.

The inks of this series may also be used for printing on the outside of food packaging and will exhibit good solvent and water resistance after 12 hours.

## 3. RANGE OF COLOURS:

The basic ink mixing system consists of 12 basic colours and may be used for the mixing of a wide colour shade range. Field proven mixing formulations exist for Pantone<sup>®</sup>, HKS, RAL, NCS, etc. (see 6.2).

## 3.1 Basic colours:

Light Yellow	G 1*	983 UV 2530
	• .	
Medium Yellow	G 2	983 UV 2531
Orange	G 3*	983 UV 30047
Light Red	G 4*	983 UV 30048
Red	G 5*	983 UV 30049
Pink	G 6	983 UV 30050
Violet	G 7	983 UV 50130
Blue	G 8	983 UV 50131
Green	G 91	983 UV 6840
Brown	G 10	983 UV 8285
White	G 11	983 UV 1177
Black	G 12	983 UV 9169
Clear Base		983 UV 0007

<sup>\*</sup> The above colours are also available in extremely light-fast versions having a value of > 7 on the blue wool scale (1-8).

## 3.2 Special Products:

#### 3.2.1 Light-fast Formulations:

Light Yellow	G 25	983 UV 2622
Orange	G 31	983 UV 30259
Light Red	G 41	983 UV 30260
Red	G 51	983 UV 30261

#### 3.2.2 High Opacity Formulations:

White	(high opacity)	983 UV 1219
Black	(high opacity)	983 UV 9224

#### 3.3 Euro-Colours / 4-Colour Process Printing Inks:

For 4-colour process printing according to DIN 16538, 4 Euro-basic colours are available:

Euro-Yellow	983 UV 2587
Euro-Magenta	983 UV 30179
Euro-Cyan	983 UV 50198
Halftone Black	983 UV 9241

#### 3.4 Bronze Colours:

see separate "Bronze Colours" leaflet

### 4. ADDITIONAL PRODUCTS:

Printing Lacquer	983 UV 0090
Matting Agent	(max. addition: 10 %) 983 UV 0161
Raster Paste	(max. addition: 10 %) 983 UV 0012

The gloss level of the ink can be varied by using the Matting Agent.

Raster paste can be added to reduce "Dot Gain" and to achieve sharper dots.

#### 5. ADDITIVES:

#### 5.1 Thinner:

The inks of the 983 UV series are ready to use. If further viscosity reduction is desired, an UV thinner may be added. In order to increase curing, the addition of reactive thinner is recommended.

In general, no solvent-based thinners should be used due to flammable nature of the solvents

UV Thinner (max. addition: 2-5 %) 983 UV 0014 Reactive Thinner (max. addition: 2-5 %) 983 UV 0010

# 983 UV SERIES

#### 5.2 Adhesion Modifiers:

In the case of particularly high resistance requirements, the addition of an adhesion modifier is recommended. However the addition of adhesion modifier to UV curable ink will lead to a processing time (potlife) of 4-8 hours at 21°C depending on the colour shade. Higher processing temperatures will result in a shorter potlife.

Overprinting must take place within 12 hours at 21°C in case an adhesion modifier is added.

Adhesion Modifier (max. add.: 2 %) HV 100 VR 1259

#### 5.3 Levelling Agent:

The levelling of the ink surface can be optimised by the use of a levelling agent.

Levelling Agent (max. add.: 0,5-1 %) VM 100 VR 1297

#### 6. PROCESSING INSTRUCTIONS:

#### 6.1 Pre-treatment:

Pre-treatment of polyolefines (PE/PP) must be performed by Flame Treatment or CORONA-discharge in order to insure the adhesion of the UV screen printing ink to the substrate. In case of PE, surface tension needs to be at least 42 mN/m (Dynes/cm), in case of PP at least 52 mN/m (Dynes/cm).

## 6.2 Stencils / Printing Equipment:

Screen printing meshes between 140-34 through 165-34 threads/cm (T-mesh) are suitable for printing with UV inks. The colour mixing formulations are based on a 165-34 threads/cm mesh. However, test prints and approval of the colour are generally recommended for the respective print job. The 983 UV series can be used with all screen-printing machines with screen printing stencils currently used for industrial applications. Any acrylic ester resistant squeegee material may be used.

## 6.3 Curing Conditions:

The varying UV absorption of the individual colours results in a range of curing properties depending on colour and opacity. All colours of the 983 UV series can be cured by the use of medium pressure mercury vapour lamps (at least 160 W/cm).

The optimum energy output is 250 - 300 Millijoule/cm<sup>2</sup>. UV curing is followed by a 12 hour post-cure phase after which the ink film is fully cured and has its final properties.

However, it must be noted, that low radiation intensity, excessive machine speeds or excessive film thickness can have a negative influence on the curing properties and adhesion.

Un-cured prints are considered a hazardous waste. Therefore, it is recommended to cure misprints under the UV lamp as a matter of principle. After curing, spoilage can be disposed by conventional methods and may be incinerated without causing any difficulties.

#### 7. CLEANING:

Screens and squeegees as well as other working materials can be cleaned with the RUCO screen cleaner 32 335. If cleaning is not performed by fully automatic cleaning equipment, protective gloves must be worn. Cleaning liquids that are contaminated with UV products should not be used for the washing of working materials that were used with conventional screen printing inks. Solvents that contain UV residue are not suitable for reclamation and must be treated as a separate waste.

Universal Cleaner UR 32 335 Cleaner for cleaning equipment WR 100 VR 1240C Bio degradable Cleaner BR 100 VR 1272

### 8. SHELF LIFE:

A shelf life of 12 months is guaranteed when storing the inks at 21°C and in the original packing container. At higher storage temperatures the shelf life will be reduced.

#### 9. PRECAUTIONS:

UV inks may cause irritations and can increase the sensitivity of the skin, possibly leading to hypersensitivity. Therefore, the use of disposable gloves and protective goggles is strongly recommended.

For further information on the safety, storage and environmental aspects concerning these products, please refer to the Material Safety Data Sheet (MSDS).

Additional technical information may be obtained from our staff of the Technical Application Department.

A.M. RAMP & Co. GmbH Lorsbacher Strasse 28 D-65817 Eppstein

Tel: ++49 (0) 6198-304-0 FAX: ++49 (0) 6198-304-287 E-Mail: info@ruco-inks.com